

<p>1. DESCRIPTION</p> <p>IMPA WB BRICK DRESSING is 100% acrylic clear coating. This product is UV-resistant, it enhance and protect interior and exterior face brick, sandstone and texture paint coatings.</p> <p>2. FEATURES</p> <ul style="list-style-type: none"> • Water based, therefore cleaning is at low cost. • Superb durability and excellent flexibility which makes it ideal for textured surfaces. • The acrylic binders impart excellent properties of weather and alkali resistance. • Ready for use. • The 100% acrylic binders ensure excellent adhesion to surfaces. <p>3. LIMITATIONS</p> <ul style="list-style-type: none"> • Avoid application to hot surfaces which may cause undue bubbling • Do not apply over other types of brick dressings or varnishes unless compatibility has been established beforehand. • Not recommended for surfaces where moisture may be absorbed from behind, such as unsealed flower boxes. • Roller application not recommended since it may cause undue bubbling. • NOT suitable as a floor dressing. <p>4. SURFACE PREPARATIONS</p> <p>All surfaces must be sound, clean, dry and free from dirt, oil, grease or any other contaminants.</p> <ul style="list-style-type: none"> • Remove cement stains and excess mortar with IMPA WB BRICK DRESSING. Rinse thoroughly and allow to dry. • UNCOATED BRICK, SLASTO AND STONE IN GOOD CONDITION: Remove any wax polish, oil, grease, dirt, saline deposits, etc. with Restore Heavy Duty Degreaser. Rinse thoroughly with clean water. Allow to dry. • SURFACES PREVIOUSLY COATED WITH BRICK AND SLASTO DRESSING Remove loose and flaking material. Remove any grease, oil, etc. with Restore Heavy Duty Degreaser. Rinse thoroughly with clean water. Allow to dry • WEATHERED BRICK, SLASTO AND STONE Remove all loose slivers, friable and powdery material. Brush off all loose dust 	<p style="text-align: center;">TRANSLUCENT SURFACE COATINGS</p> <p style="text-align: center;">IMPA WB BRICK DRESSING</p> <p style="text-align: center;">ISSUED DATE: JUNE 2014 REV1</p> <p style="text-align: center;">TECHNICAL DATA</p> <table border="1"> <tr> <td><i>Product Code</i></td> <td>PR1022</td> </tr> <tr> <td><i>Colour</i></td> <td>Clear</td> </tr> <tr> <td><i>Appearance</i></td> <td>Gloss</td> </tr> <tr> <td><i>Shelf life</i></td> <td>12 Months</td> </tr> <tr> <td><i>Packaging</i></td> <td>1L, 5L & 20L</td> </tr> <tr> <td><i>Flashpoint</i></td> <td>Non Flammable</td> </tr> <tr> <td><i>Viscosity</i></td> <td>55 – 60KU/23°C</td> </tr> <tr> <td><i>S.G (weight)</i></td> <td>0.96 – 1,02kg/l</td> </tr> <tr> <td><i>Solids per volume</i></td> <td>27 - 29%</td> </tr> <tr> <td><i>Solids per mass</i></td> <td>30 – 32%</td> </tr> <tr> <td><i>Practical Spreading rate (depending on porosity)</i></td> <td>12m²/L per coat @ 25µm DFT</td> </tr> <tr> <td><i>Recommended finishing coats.</i></td> <td>1</td> </tr> <tr> <td>DRYING TIME</td> <td></td> </tr> <tr> <td><i>Touch dry time</i></td> <td>30min at 23°C</td> </tr> <tr> <td><i>Recoating Time</i></td> <td>1Hour at 23°C</td> </tr> <tr> <td><i>Full cure</i></td> <td>4-7 Days</td> </tr> <tr> <td>APPLICATION</td> <td></td> </tr> <tr> <td><i>Roller & Brush</i></td> <td>Ready for use</td> </tr> <tr> <td><i>Spray</i></td> <td>Dilute not more than 10% with clean water</td> </tr> <tr> <td><i>Cleaning</i></td> <td>Warm water and soap</td> </tr> <tr> <td><i>Mixing</i></td> <td>Stir until homogeneous Stir occasionally during use</td> </tr> </table>	<i>Product Code</i>	PR1022	<i>Colour</i>	Clear	<i>Appearance</i>	Gloss	<i>Shelf life</i>	12 Months	<i>Packaging</i>	1L, 5L & 20L	<i>Flashpoint</i>	Non Flammable	<i>Viscosity</i>	55 – 60KU/23°C	<i>S.G (weight)</i>	0.96 – 1,02kg/l	<i>Solids per volume</i>	27 - 29%	<i>Solids per mass</i>	30 – 32%	<i>Practical Spreading rate (depending on porosity)</i>	12m ² /L per coat @ 25µm DFT	<i>Recommended finishing coats.</i>	1	DRYING TIME		<i>Touch dry time</i>	30min at 23°C	<i>Recoating Time</i>	1Hour at 23°C	<i>Full cure</i>	4-7 Days	APPLICATION		<i>Roller & Brush</i>	Ready for use	<i>Spray</i>	Dilute not more than 10% with clean water	<i>Cleaning</i>	Warm water and soap	<i>Mixing</i>	Stir until homogeneous Stir occasionally during use
<i>Product Code</i>	PR1022																																										
<i>Colour</i>	Clear																																										
<i>Appearance</i>	Gloss																																										
<i>Shelf life</i>	12 Months																																										
<i>Packaging</i>	1L, 5L & 20L																																										
<i>Flashpoint</i>	Non Flammable																																										
<i>Viscosity</i>	55 – 60KU/23°C																																										
<i>S.G (weight)</i>	0.96 – 1,02kg/l																																										
<i>Solids per volume</i>	27 - 29%																																										
<i>Solids per mass</i>	30 – 32%																																										
<i>Practical Spreading rate (depending on porosity)</i>	12m ² /L per coat @ 25µm DFT																																										
<i>Recommended finishing coats.</i>	1																																										
DRYING TIME																																											
<i>Touch dry time</i>	30min at 23°C																																										
<i>Recoating Time</i>	1Hour at 23°C																																										
<i>Full cure</i>	4-7 Days																																										
APPLICATION																																											
<i>Roller & Brush</i>	Ready for use																																										
<i>Spray</i>	Dilute not more than 10% with clean water																																										
<i>Cleaning</i>	Warm water and soap																																										
<i>Mixing</i>	Stir until homogeneous Stir occasionally during use																																										

5. APPLICATION

- Ready for use for application by brush and airless spray to non-porous surfaces (e.g. face brick and ornament stone) Always apply a liberal wet coat to penetrate fine cracks and porous areas. Remove bubbles that may form.
- One coat is usually sufficient for non-porous surfaces such as face brick and ornamental stone. Porous surfaces require a second coat.
- **Make sure to brush out any ponding material that may be created when applying on rough surfaces to ensure product dry to a clear coating.**

6. PRECAUTION

- Application should be avoided in cold and moist weather conditions.
- **Do Not** apply the product at surface temperatures below 6°C (minimum of 2°C above dew point) and temperatures above 40°C
- **Do Not** apply if ambient temperature is less than 10°C or more than 40°C.
- **Do Not** apply if relative humidity temperature is less than 10°C or more than 85. °C
- When **WB BRICK DRESSING** is applied to textured surfaces or face brick: - be sure to reduce film built in such a way that white colouring does not take place. Application by brush is recommended.
- **WB BRICK DRESSING** is suitable for interior and exterior application
- **WB BRICK DRESSING** is not recommended for use over solvent based alkyd paints
- Keep out of reach of children
- Ensure good ventilation during application and drying
- In case of skin contact, wash with soap and water or a recognized skin cleaner
- Avoid contact with eyes – in case of contact, rinse eyes immediately with plenty of water and seek medical advice if symptoms persist.
- Harmful if swallowed. Do not induce vomiting. Seek medical attention
- Refer to Material Safety data Sheet for complete information

Environmental Health & Safety Information

WARNING! IRRITANT! HARMFUL IF SWALLOWED. CONTAINS: PROPYLENE OR ETHYLENE GLYCOL. MAY CAUSE EYE, NOSE AND THROAT IRRITATION. AVOID CONTACT WITH SKIN AND EYES AND AVOID BREATHING OF VAPORS AND SPRAY MIST. WEAR EYE PROTECTION AND PROTECTIVE CLOTHING. USE ONLY WITH ADEQUATE VENTILATION. To avoid breathing vapours and spray mist, open windows and doors or use other means to ensure fresh air entry during application and drying. If you experience eye watering, headaches or dizziness, increase fresh air. If properly used, a respirator (NIOSH approved for organic vapor with P series particulate pre-filter) may offer additional protection; obtain professional advice before using. A dust mask does not provide protection against vapors. Avoid contact with eyes and skin. Wash thoroughly after handling. Close container after each use. **FIRST AID:** If you experience difficulty in breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical assistance immediately. In case of eye contact, flush immediately with plenty of water for at least 15 minutes and get medical attention; for skin, wash thoroughly with soap and water. If swallowed, get medical attention immediately.

CAUTION: KEEP OUT OF REACH OF CHILDREN AND ANIMALS - DO NOT TAKE INTERNALLY.

Refer to Material Safety Data Sheet for additional health and safety information.

IN CASE OF FIRE: Use foam, CO₂, dry chemical, or water fog.

SPILL – Absorb with inert material and dispose of as specified under Thinning/Clean-up.

† **WARNING!** If you scrape, sand or remove old paint, you may release lead dust.

DISCLAIMER

The technical information contained in this document are given in good faith and are meant to be used as a guideline by the specifier or user. Whilst we are confident about the quality of our products, we cannot accept any liability for the incorrect use or application of our products. Surface preparation forms an integral part of the scope of works and it is expected that the highest standards are maintained during surface preparation and application, to ensure that our products perform as intended. Always ensure to use the same product batch numbers, refrain from doing spot touch-ups and paint surfaces from corner to corner to prevent colour and sheen variance. As technology may change over time we reserve the right to change products to keep up with changes in raw materials or product trends without pre notice. Although we will always prevail to keep clients informed about changes to be made, but cannot bind ourself to such notes Please ensure the use of the latest Technical Data Sheet.

Please note: that all our latest Product Data Sheets and Material Safety Data Sheets are available for viewing on our website at www.impa.co.za. All information listed is owned or used under licence of Impa Paints and its related companies. © 2010 Lurama 149 (Pty) Ltd. All rights is reserved.