

## PRODUCT DATA SHEET

## 1. DESCRIPTION

**Impa QD LS Primer** is a one component, solvent base, modified styrenated alkyd resin, air drying pigmented primer.

A fast drying primer for use under Impa QD Enamel Range and other industrial topcoats.

Suitable for inland and coastal environments.

### 2. FEATURES

- Dries to a good quality, tough and durable finish.
- It has a very even flow and excellent leveling
- Easy application and rapid drying to a gloss finish.
- Not resistant to strong acids and alkalis outside ph range of 6-9.

#### 3. RECOMMENDED PRIMER

• Steel: No primer needed

### 4. MIXING

 Stir the base component well with a flat – bottomed paddle or mechanical mixer until product is uniform

## 5. PREPARATION OF SURFACES

- Surfaces must be clean, sound and dry
- Remove grease and oil with Impa Degreasing Solvent
- Grind and fettle weld spatter, protrusions and sharp edges to a minimum radius of 2mm
- All surfaces shall be abrasive blast cleaned to grade SA 2½ of standard ISO 8501-1 with a blast profile 30-40µM. The coating must be applied before any flash rusting occurs or the surface shall be re-blast cleaned again.
- Alternatively abrade the surface thoroughly using grinding disks to achieve a similar profile.

# SOLVENTBASE PRIMERS

## **IMPA QD LS PRIMER**

ISSUED DATE: JUNE 2014 Rev 1

	$\sim$		. ^		_		- 4
TE	( ' Þ	4 NI	" "	ΔI	- 11	Δ	IΛ
16	vI	111	ıv	~L		$\boldsymbol{\wedge}$	_

Product Code	PI2036			
Colour	Red Oxide.			
Appearance	Semi Gloss			
Shelf life	12 Months			
Packaging	20L & 200L			
Flashpoint	4°C			
Viscosity	40 – 60 Sec/4mm –Cup DIN53211			
S.G (weight)	0,91kg/L			
Solids per volume	16 – 18%			
Solids per mass	24 – 26%			
VOC				
Practical Spreading rate				
(depending on porosity)	6m²/L @ 25μm, DFT			
5				
Recommended finishing coats.	1			
DRYING TIME				
Temperature Resistance	Dry 80°C			
Touch dry time	15 Min at 23°C for 25µm @, 65%RH			
Recoating Time	2 Hours at 23°C @, 65% RH			
Full Cure	4-7 Days			
	·			
APPLICATION				
Spray Airless	Ready for use			
	Pump Ratio: 30 to 1Min.			
	Nozzle Orifice: 11 to 15 Thou			
	Tip Pressure: 145 Bar Min			
Conventional Spray	Pressure & Gravity Feed. Pressure as			
	needed.			
Cleaning & Thinning	Impa E Thinnors may 50/			
Cleaning & Hillining	Impa E Thinners max 5%			





## PRODUCT DATA SHEET

### 6. PRECAUTIONS.

- Application should be avoided in cold and moist weather conditions.
- Do Not apply the product at surface temperatures below 6°C (minimum of 2°C above dew point) and temperatures above 40°C
- Do Not apply if ambient temperature is less than 10°C or more than 40°C.
- Do Not apply if relative humidity temperature is less than 10°C or more than 85. °C
- Extremely cold conditions will make the drying time longer.
- Paint in area where there is good ventilation
- Containing inflammable solvents
- Avoid contact with skin by using gloves, barrier creams and face mask.
- Must be over coated to provide corrosion resistance.

Environmental Health & Safety Information
WARNING! IRRITANT! HARMFUL IF SWALLOWED. CONTAINS: LOW & HIGH AROMATIC SOLVENTS. MAY CAUSE EYE, NOSE AND THROAT IRRITATION. AVOID CONTACT WITH SKIN AND EYES AND AVOID BREATHING OF VAPORS AND SPRAY MIST. WEAR EYE PROTECTION AND PROTECTIVE CLOTHING. USE ONLY WITH ADEQUATE VENTILATION. To avoid breathing vapours and spray mist, open windows and doors or use other means to ensure fresh air entry during application and drying. If you experience eye watering, headaches or dizziness, increase fresh air. If properly used, a respirator (NIOSH approved for organic vapor with P series particulate pre-filter) may offer additional protection; obtain professional advice before using. A dust mask does not provide protection against vapors. Avoid contact with eyes and skin. Wash thoroughly after handling. Close container after each use. FIRST AID: If you experience difficulty in breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical assistance immediately. In case of eye contact, flush immediately with plenty of water for at least 15 minutes and get medical attention; for skin, wash thoroughly with soap and water. If swallowed, get medical attention immediately.

CAUTION: KEEP OUT OF REACH OF CHILDREN AND ANIMALS - DO NOT TAKE INTERNALLY.

Refer to Material Safety Data Sheet for additional health and safety information IN CASE OF FIRE: Use foam, CO2, dry chemical, or water fog.

SPILL – Absorb with inert material and dispose of as specified under Thinning/Clean-up. † WARNING! If you scrape, sand or remove old paint, you may release lead dust.

#### DISCLAIMER

The technical information contained in this document are given in good faith and are meant to be used as a guideline by the specifier or user. Whilst we are confident about the quality of our products, we cannot accept any liability for the incorrect use or application of our products. Surface preparation forms an integral part of the scope of works and it is expected that the highest standards are maintained during surface preparation and application, to ensure that our products perform as intended. Always ensure to use the same product batch numbers, refrain from doing spot touch-ups and paint surfaces from corner to corner to prevent colour and sheen variance. As technology may change over time we reserve the right to change products to keep up with changes in raw materials or product trends without pre notice. Although we will always privail to keep clients informed about changes to be made, but cannot bind ourself to such notes Please ensure the use of the latest Technical

Data Sheet.

Please note: that all our latest Product Data Sheets and Material Safety Data Sheets are available for viewing on our website at <a href="www.impa.co.za">www.impa.co.za</a>. All information listed is owned or used under licence of Impa Paints and its related companies. © 2010 Lurama 149 (Pty) Ltd. All rights is reserved