

1. DESCRIPTION

Impa QD HS Primer is a one component, solvent base, modified styrenated alkyd resin, air drying pigmented primer.

A fast drying primer for use under Impa QD Enamel Range and other industrial topcoats.

Suitable for inland and coastal environments.

2. FEATURES

- Dries to a good quality, tough and durable finish.
- It has a very even flow and excellent leveling
- Easy application and rapid drying to a gloss finish.
- Not resistant to strong acids and alkalis outside pH range of 6-9.

3. RECOMMENDED PRIMER

- **Steel:** No primer needed

4. MIXING

- Stir the base component well with a flat – bottomed paddle or mechanical mixer until product is uniform

5. PREPARATION OF SURFACES

- Surfaces must be clean, sound and dry
- Remove grease and oil with Impa Degreasing Solvent
- Grind and fettle weld spatter, protrusions and sharp edges to a minimum radius of 2mm
- All surfaces shall be abrasive blast cleaned to grade SA 2½ of standard ISO 8501-1 with a blast profile 30-40µm. The coating must be applied before any flash rusting occurs or the surface shall be re-blast cleaned again.
- Alternatively abrade the surface thoroughly using grinding disks to achieve a similar profile.

SOLVENTBASE PRIMER

IMPA QD HS PRIMER

ISSUED DATE: JUNE 2014 Rev 1

TECHNICAL DATA

Product Code	PI2034
Colour	Red Oxide.
Appearance	Matt
Shelf life	12 Months
Packaging	20L & 200L
Flashpoint	4°C
Viscosity	40 – 60 Sec/4mm –Cup DIN53211
S.G (weight)	1,16kg/L
Solids per volume	31 – 32%
Solids per mass	49 – 50%
Practical Spreading rate (depending on porosity)	6m²/L @ 35µm, DFT
Recommended finishing coats. Film Thickness	1 Wet 166µ & Dry 50µm
DRYING TIME	
Temperature Resistance	Dry 80°C
Touch dry time	15 Min at 23°C for 50µm @ 65%RH
Recoating Time	2 Hours at 23°C @ 65% RH
Full Cure	4-7 Days
APPLICATION	
Spray Airless	Ready for use Pump Ratio: 30 to 1Min. Nozzle Orifice: 11 to 15 Thou Tip Pressure: 145 Bar Min Pressure & Gravity Feed. Pressure as needed.
Conventional Spray	
Cleaning & Thinning	Impa E Thinners max 5%

6. PRECAUTIONS.

- Application should be avoided in cold and moist weather conditions.
- **Do Not** apply the product at surface temperatures below 6°C (minimum of 2°C above dew point) and temperatures above 40°C
- **Do Not** apply if ambient temperature is less than 10°C or more than 40°C.
- **Do Not** apply if relative humidity temperature is less than 10°C or more than 85. °C
- Extremely cold conditions will make the drying time longer.
- Paint in area where there is good ventilation
- Containing inflammable solvents
- Avoid contact with skin by using gloves, barrier creams and face mask.
- Must be over coated to provide corrosion resistance.

Environmental Health & Safety Information

WARNING! IRRITANT! HARMFUL IF SWALLOWED. CONTAINS: LOW & HIGH AROMATIC SOLVENTS. MAY CAUSE EYE, NOSE AND THROAT IRRITATION. AVOID CONTACT WITH SKIN AND EYES AND AVOID BREATHING OF VAPORS AND SPRAY MIST. WEAR EYE PROTECTION AND PROTECTIVE CLOTHING. USE ONLY WITH ADEQUATE VENTILATION. To avoid breathing vapours and spray mist, open windows and doors or use other means to ensure fresh air entry during application and drying. If you experience eye watering, headaches or dizziness, increase fresh air. If properly used, a respirator (NIOSH approved for organic vapor with P series particulate pre-filter) may offer additional protection; obtain professional advice before using. A dust mask does not provide protection against vapors. Avoid contact with eyes and skin. Wash thoroughly after handling. Close container after each use. **FIRST AID:** If you experience difficulty in breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical assistance immediately. In case of eye contact, flush immediately with plenty of water for at least 15 minutes and get medical attention; for skin, wash thoroughly with soap and water. If swallowed, get medical attention immediately.

CAUTION: KEEP OUT OF REACH OF CHILDREN AND ANIMALS - DO NOT TAKE INTERNALLY.

Refer to Material Safety Data Sheet for additional health and safety information.

IN CASE OF FIRE: Use foam, CO2, dry chemical, or water fog.

SPILL – Absorb with inert material and dispose of as specified under **Thinning/Clean-up**.

† **WARNING!** If you scrape, sand or remove old paint, you may release lead dust.

DISCLAIMER

The technical information contained in this document are given in good faith and are meant to be used as a guideline by the specifier or user. Whilst we are confident about the quality of our products, we cannot accept any liability for the incorrect use or application of our products. Surface preparation forms an integral part of the scope of works and it is expected that the highest standards are maintained during surface preparation and application, to ensure that our products perform as intended. Always ensure to use the same product batch numbers, refrain from doing spot touch-ups and paint surfaces from corner to corner to prevent colour and sheen variance. As technology may change over time we reserve the right to change products to keep up with changes in raw materials or product trends without pre notice. Although we will always privial to keep clients informed about changes to be made, but cannot bind ourself to such notes Please ensure the use of the latest Technical Data Sheet.

Please note : that all our latest Product Data Sheets and Material Safety Data Sheets are available for viewing on our website at www.impa.co.za. All information listed is owned or used under licence of Impa Paints and its related companies. © 2010 Lurama 149 (Pty) Ltd. All rights is reserved.